

WEROTECH

UNIVERSAL ROLLER COVERINGS FOR DRAW, IDLER AND CONTACT ROLLERS

PRODUCT PORTFOLIO

Compound	Sh A	Color	EL. Properties	Max.°C	MO	O ₃	ELA	E/K	AB
					●	●	●	●	●
WEROTECH									
D600-01	60	graphite black	conductive	130	3	1	1	1	3
B605-01	60	graphite black	conductive	80	3	3	3	3	1
D651-01	65	graphite black	conductive	130	3	2	2	1	2
E650-01	65	graphite black	dissipative	120	1	1	3	3	2
C701-01	70	graphite black	isolating	120	1	3	3	3	2
D751-01	75	graphite black	conductive	130	3	1	1	1	1
B759-01	75	graphite black	isolating	80	3	3	3	3	2
M802-01	80	graphite black	isolating	130	2	1	3	3	2
E851-01	85	graphite black	dissipative	120	2	1	3	2	3

● = Chemical Resistance : MO = Mineral Oil | O₃ = Ozone | E/K = Esters/Ketones 1 = resistant | 2 = resistant with restrictions | 3 = not resistant
 ● = Physical Properties : ELA = Elasticity | AB = Abrasion Resistance 1 = very good | 2 = good | 3 = moderate
 Electric (EL) Properties : Conductive < 10⁴Ω | Dissipative < 10⁸Ω | Isolating > 10¹⁴Ω.
 The electrical resistance was tested on a laboratory sample and does not match the value of the rubberized roller.

Liability exclusion

The above information is based on our knowledge and experience under normal conditions, assuming the product is stored and used properly. This data is understood as the characterization of the material properties and not as minimum values in terms of specification. Technical changes reserved.