

WEROLACK

ROLLER COVERINGS FOR TRANSFER AND COATING APPLICATION ROLLERS

PRODUCT PORTFOLIO

Compound	Sh A	Color	EL. Properties	Max.°C	MO	O ₃	ELA	E/K	AB
WEROLACK									
D302-02	30	graphite black	insulating	130	3	1	1	1	N/A
D359-11	35	light pink	insulating	130	3	1	1	1	N/A
D409-54	40	ocean blue	insulating	130	3	1	1	1	N/A
D551-12	55	stone grey	insulating	130	3	1	1	1	3
D552-01	55	graphite black	dissipative	130	3	1	1	1	2
M652-01	65	graphite black	dissipative	130	2	1	3	3	1
D659-70	65	traffic green	insulating	130	3	1	1	1	2
D701-54	70	ocean blue	insulating	130	3	1	1	1	2
D801-54	80	ocean blue	insulating	130	3	1	2	1	3

● = Chemical Resistance : MO = Mineral Oil | O₃ = Ozone | E/K = Esters/Ketones 1 = resistant | 2 = resistant with restrictions | 3 = not resistant
 ● = Physical Properties : ELA = Elasticity | AB = Abrasion Resistance 1 = very good | 2 = good | 3 = moderate
 Electric (EL) Properties : Conductive < 10⁴ Ω | Dissipative < 10⁸ Ω | Isolating > 10¹⁴ Ω.
 The electrical resistance was tested on a laboratory sample and does not match the value of the rubberized roller.

Liability exclusion

■ The above information is based on our knowledge and experience under normal conditions, assuming the product is stored and used properly. This data is understood as the characterization of the material properties and not as minimum values in terms of specification. Technical changes reserved.